OSLO PRODUCT DATA SHEET



- 1	Range	Oslo
and the second s	Category	Wood, Floor Tiles, PTV 36+
		Tiles
and the second	Collection	Absolute Collection
	Short Code	OSL03N
5	Colour	Aged Grey
	Finish	Natural
	Wall Suitability	Internal & External
	Floor Suitability	Internal Only
	Wet Barefoot	-
	Material	Glazed Porcelain
	Classificiation	Bla
	Light Reflectance Value	42.00
	CSV	V3
	PTV (96)	Wet 36+ Dry 36+
	PTV (55)	-
	R Value	10
	Wet Ramp	Α
	PEI	IV
	Traffic	Commercial

 ${\cal O}$ Recycled Content

Up to 30%

Physical Properties				
「est / Standard		Requirement	Test Result	
EN ISO 1		±0.6%≤ ± 2mm	Pass	
→ Thicknes ↑ EN ISO I	-	±5%≤ ± 0.5mm	Pass	
- Straight EN ISO I	n ess of Sides 0545-2	±0.5% ≤ ± 1.5mm	Pass	
- Rectang EN ISO I		±0.5% ≤ ± 2mm	Pass	
→ Surface I ↑ ↑ EN ISO I		±0.5% ≤ ± 2mm	Pass	
Water A EN ISO I	osorption 0545-3	≤0.5%	≤0.5%	
Modulus EN ISO I	of Rupture 0545-4	≥35N/mm²	≥35N/mm²	
Thermal EN ISO I		Pass	Pass	
Frost Re EN ISO I		Resistant	Resistant	
Chemica EN ISO I	l Resistance 0545-13	Min Class B	Class B	
Stain Res EN ISO I		Min Class 3	Class 5	
Fire Rati Not Appl	-	N/A	Class A I FL Non Combustible	
kg Weight/ Thicknes			19.1kg 24.3kg	

Samples Service

Available Sizes

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | Fax: +44 (0) | 782 577 379 Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (17/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.

