OSLO PRODUCT DATA SHEET



And a second sec	Range	Oslo
	Category	Wood, Floor Tiles, PTV 36+
		Tiles
	Collection	Absolute Collection
	Short Code	OSL04G
	Colour	Carbon Grey
	Finish	Grip
	Wall Suitability	Internal & External
	Floor Suitability	Internal & External
	Wet Barefoot	Yes
	Material	Glazed Porcelain
	Classificiation	Bla
	Light Reflectance Value	15.00
	CSV	V3
	PTV (96)	Wet 36+ Dry 36+
	PTV (55)	Wet 36+
	R Value	11
	Wet Ramp	В
	PEI	IV
	Traffic	Commercial

 ${\cal O}$ Recycled Content

Up to 30%

Physical Properties	B	T . D . I.
Test / Standard	Requirement	Test Result
Length/Width	±0.6%≤ ± 2mm	Pass
EN ISO 10545-2	10.0/02 1 2000	1 455
↓ Thickness	±5%≤ ± 0.5mm	Pass
1 EN ISO 10545-2	±5%≤±0.5mm	Pass
Straightness of Sides	±0.5% ≤ ± 1.5mm	Pass
EN ISO 10545-2	±0.5% S ± 1.5mm	Pass
Rectangularity	±0.5% ≤ ± 2mm	Pass
EN ISO 10545-2	10.3 % S 1 2mm	Pass
↓ Surface Flatness	±0.5% ≤ ± 2mm	Pass
1 1 EN ISO 10545-2	10.3 % S 1 2mm	Pass
Water Absorption	≤0.5%	≤0.5%
EN ISO 10545-3	20.3%	20.3 %
Modulus of Rupture	≥35N/mm²	≥35N/mm²
EN ISO 10545-4	25514/1111	25514/11111
Thermal Shock	Pass	Pass
EN ISO 10545-9	r dSS	Fass
* Frost Resistance	Resistant	Resistant
EN ISO 10545-12	Resistant	Resistant
Chemical Resistance	Min Class B	Class B
EN ISO 10545-13	Min Class D	Class D
Stain Resistance	Min Class 3	Class 5
EN ISO 10545-14	Min Class 5	Class 5
Fire Rating	N/A	Class A I FL Non
Not Applicable	IN/A	Combustible
kg Weight/m ²		
Thickness: 9mm		19.1kg
Thickness: 10.5mm		24.3kg

Email: techadvice@johnson-tiles.com

Available Sizes

Samples Service Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (17/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.

JOHNSON TILES