OTTAWA PRODUCT DATA SHEET





Available Sizes

300x300x10.5mm (50x50mm)

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379

Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

	Up to 30%	
Range	Ottawa	
Category	Stone, Floor Tiles	
Collection	Absolute Collection	
Short Code	OTAINM	
Colour	White	
Finish	Natural - Square Mosaic	
Wall Suitability	Internal & External	
Floor Suitability	Internal Only	
Wet Barefoot	-	
Material	Glazed Porcelain	
Classificiation	Bla	
Light Reflectance Value	55.00	
CSV	V3	
PTV (96)	Wet 0-24 Dry 36+	
PTV (55)	-	
R Value	-	
Wet Ramp	-	
PEI	IV	
Traffic	Commercial	

Physical Properties				
Test / Standard Requir		Requirement	Test Result	
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	±0.3%	
→	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	±3%	
-]+	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	±0.3%	
	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.3%	
\downarrow	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.3%	
	Water Absorption EN ISO 10545-3	≤0.5%	≤0.1%	
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥35N/mm²	
	Thermal Shock EN ISO 10545-9	Pass	Pass	
*	Frost Resistance EN ISO 10545-12	Resistant	Resistant	
	Chemical Resistance EN ISO 10545-13	Min Class B	Class A	
	Stain Resistance EN ISO 10545-14	Min Class 3	Pass	
\$\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\	UV Colour Resistance		Unaffected by light	
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible	
kg	Weight/m² Thickness:9mm		24.51kg	

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance as the variation of the standard production value. Please note, Inadequate cleaning and maintenance of slip like as to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a line of the slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (09/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 1560/0437 @ 2025 in Johnson Tiles All rights reserved.

