## **OXFORD PRODUCT DATA SHEET**



Δva	ila	hle	Sizes	

200x200x8.5mm

## Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379

Email: samples@johnson-tiles.com

## Technical Helpline

Tel: +44 (0) | 782 524 | | | | Fax: +44 (0) | 782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Range	Oxford	
Category	Colour, Pattern, Floor	
	Tiles, PTV 36+ Tiles	
Collection	Absolute Collection	
Short Code	OXF01N	
Colour	White	
Finish	Natural	
Wall Suitability	Internal & External	
Floor Suitability	Internal Only	
Wet Barefoot	-	
Material	Glazed Porcelain	
Classificiation	Bla	
Light Reflectance Value	72.00	
CSV	VI	
PTV (96)	Wet 36+ Dry 36+	
PTV (55)	-	
R Value	-	
Wet Ramp	-	
PEI	IV	
Traffic	Commercial	

Physical Properties					
Test / Standard	Requirement	Test Result			
Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass			
Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass			
Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass			
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass			
Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass			
Water Absorption EN ISO 10545-3	≤0.5%	≤0.5%			
Modulus of Rupture EN ISO 10545-4	≥35N/mm²	Pass			
Thermal Shock EN ISO 10545-9	Pass	Pass			
Frost Resistance EN ISO 10545-12	Resistant	Resistant			
Chemical Resistance EN ISO 10545-13	Min Class B	Pass			
Stain Resistance EN ISO 10545-14	Min Class 3	Pass			
UV Colour Resistance		Unaffected by light			
Fire Rating Not Applicable	N/A	Class A I FL Non Combustible			
kg Weight/m² Thickness: 8.5mm		18.34kg			

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a lips slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (09/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in Englanc No. 15600437. © 2025 Johnson Tiles. All rights reserved.

