## PUNTO PRODUCT DATA SHEET



		PTV 36+ Tiles
	Collection	Absolute Collection
	Short Code	PUNOIG
	Colour	White
	Finish	Grip
	Wall Suitability	Internal & External
	Floor Suitability	Internal & External
	Wet Barefoot	Yes
	Material	Glazed Porcelain
	Classificiation	Bla
	Light Reflectance Value	64.00
	CSV	V2
	PTV (96)	Wet 36+ Dry 36+
	PTV (55)	Wet 36+
043 379	R Value	11
nson-tiles.com	Wet Ramp	-
111	PEI	IV
379 hnson-tiles.com	Traffic	Commercial

Range Category Up to 10%

Stone, Speckle, Floor Tiles,

Punto

•	cal Properties Standard	Requirement	<b>Test Result</b>
Test/			
$   \uparrow \downarrow \rangle$	Length/Width	±0.6%≤ ± 2mm	Pass
	EN ISO 10545-2		
↓	Thickness	±5%≤ ± 0.5mm	Pass
$\uparrow$	EN ISO 10545-2	10/02 1 0.011111	1 435
[]_	Straightness of Sides		Pass
	EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass
П	Rectangularity		
$\sim$	EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
.l.	Surface Flatness		
$\overset{\bullet}{\frown}$	EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
	Water Absorption		
	EN ISO 10545-3	≤0.5%	≤0.5%
Ĺ	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥35N/mm²
No.	Thermal Shock	Pass	Pass
	EN ISO 10545-9		
業	Frost Resistance	Resistant	Resistant
	EN ISO 10545-12		
JA-	Chemical Resistance	Min Class B	Class A
	EN ISO 10545-13	Min Class D	Class A
A	Stain Resistance		<b>a</b> , <b>z</b>
	EN ISO 10545-14	Min Class 3	Class 5
<i>"</i> ~4,			
	UV Colour Resistance		Unaffected by light
20-	Fire Rating		Class A I FL Non
Not Applicable	N/A	Combustible	
	Weight/m <sup>2</sup>		
kg	weight/m		

## Samples Service

Available Sizes 660x660x10mm

250x250x10mm

Tel: +44 (0) | 782 524 043 Fax: +44 (0) | 782 577 379 Email: samples@johnson-tiles.com

## Technical Helpline

Tel: +44 (0) | 782 524 | | | Fax: +44 (0) | 782 577 379 Email: techadvice@johnson-tiles.co

## www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 – 24 represents a high slip potential. J2 – 35 signifies a moderate slip potential and 36'r represents a low slip potential. All rigures are accurate at the time of this data sheets creation (01/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 SJZ. Registered in Englance

