REBUS PRODUCT DATA SHEET





Available Sizes 600x600x10mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379

Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

	Up to 30%	
Range	Rebus	
Category	Concrete, Floor Tiles, PTV	
	36+ Tiles	
Collection	Absolute Collection	
Short Code	REB03G	
Colour	Pebble	
Finish	Grip	
Wall Suitability	Internal & External	
Floor Suitability	Internal & External	
Wet Barefoot	Yes	
Material	Porcelain	
Classificiation	Bla	
Light Reflectance Value	24.00	
CSV	V2	
PTV (96)	Wet 36+ Dry 36+	
PTV (55)	Wet 36+	
R Value	11	
Wet Ramp	С	
PEI	-	
Traffic	Commercial	

Physical Properties			
Test / Standa	rd	Requirement	Test Result
	n/Width 0 10545-2	±0.6%≤ ± 2mm	Pass
Thickr EN ISC	ness) 10545-2	±5%≤ ± 0.5mm	Pass
	htness of Sides 0 10545-2	±0.5% ≤ ± 1.5mm	Pass
	ngularity 0 10545-2	±0.5% ≤ ± 2mm	Pass
	e Flatness 0 10545-2	±0.5% ≤ ± 2mm	Pass
()	Absorption 0 10545-3	≤0.5%	≤0.1%
	us of Rupture 0 10545-4	≥35N/mm²	≥45N/mm²
3/18	nal Shock 0 10545-9	Pass	Pass
- 7K	Resistance 0 10545-12	Resistant	Resistant
	ical Resistance 0 10545-13	Min Class B	Class B
	Resistance 0 10545-14	Min Class 3	Min Class 3
Fire Ra	nting oplicable	N/A	Class A I FL Non Combustible
	t/m² ess: 10mm ess: 20mm		23.1kg 46.3kg

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, hadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate by potential and 364 represents a low slip potential. All figures are accurate at the time of this data sheets creation (30/04/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in Englanc No. 156/0447 @ 2075 | Ohnson Tiles All rights reserved

