REFINE PRODUCT DATA SHEET





Available Sizes

600x300x9mm 1200x600x9mm 900x450x9mm 600x100x9mm 600x600x9mm 900x900x9mm 1200x1200x9mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | | Fax: +44 (0) | 782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

${oldsymbol{arrho}}$ Recycled Content	Up to 30%	
Range	Refine	
Category	Stone, Floor Tiles, PTV 36+	
	Tiles	
Collection	Absolute Collection	
Short Code	REF03G	
Colour	Lavastone	
Finish	Grip	
Wall Suitability	Internal & External	
Floor Suitability	Internal & External	
Wet Barefoot	Yes	
Material	Porcelain	
Classificiation	Bla	
Light Reflectance Value	18.00	
CSV	V2	
PTV (96)	Wet 36+ Dry 36+	
PTV (55)	Wet 36+	
R Value	11	
Wet Ramp	С	
PEI	-	
Traffic	Commercial	

Physical Properties			
Test / Standard Requirement		Test Result	
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass
→	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass
	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass
-	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
$ \\ \boxed{ \uparrow \uparrow }$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
	Water Absorption EN ISO 10545-3	≤0.5%	≤0.5%
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥35N/mm²
	Thermal Shock EN ISO 10545-9	Pass	Pass
*	Frost Resistance EN ISO 10545-12	Resistant	Resistant
	Chemical Resistance EN ISO 10545-13	Min Class B	Pass
	Stain Resistance EN ISO 10545-14	Min Class 3	Class 5
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible
kg	Weight/m ² Thickness: 6mm Thickness: 9mm Thickness: 20mm		14.09kg 21.19kg 45.85kg

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential. 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (30/04/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 51/2. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.

