REFINE PRODUCT DATA SHEET

				1		
					a second	· vij
					K	

${\mathscr O}$ Recycled Content	Up to 30%
Range	Refine
Category	Stone, Mosaic, Floor Tile
Collection	Absolute Collection
Short Code	REF3NM
Colour	Lavastone
Finish	Natural - 25mm Square
	Mosaic
Wall Suitability	Internal & External
Floor Suitability	Internal Only
 Wet Barefoot	-
Material	Porcelain
Classificiation	Bla
Light Reflectance Value	18.00
CSV	V2
PTV (96)	Wet 25-35 Dry 36+
 PTV (55)	-
R Value	9
 Wet Ramp	A
PEI	-
Traffic	Commercial

Physical Properties			
est / Standard	Requirement	Test Result	
Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass	
	±5%≤ ± 0.5mm	Pass	
Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass	
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
◆ ↑ ↑ Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
Water Absorption EN ISO 10545-3	≤0.5%	≤0.5%	
Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥35N/mm²	
Thermal Shock EN ISO 10545-9	Pass	Pass	
Frost Resistance EN ISO 10545-12	Resistant	Resistant	
Chemical Resistance EN ISO 10545-13	Min Class B	Pass	
Stain Resistance EN ISO 10545-14	Min Class 3	Class 5	
Fire Rating Not Applicable	N/A	Class A I FL Non Combustible	
kg Thickness: 6mm Thickness: 9mm Thickness: 20mm		14.09kg 21.19kg 45.85kg	

Samples Service

Available Sizes

300x300x9mm (25x25mm)

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | Fax: +44 (0) | 782 577 379 Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (09/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.

