ROKER PRODUCT DATA SHEET



arnothing Recycled Content	Up to 20%	
Panga	Roker	
Range	Koker	
Category		
Collection	Minton Hollins Collection	
Short Code	ROSBIA	
Colour	Scuba Blue	
Finish	Gloss	
Wall Suitability	Internal Only	
Floor Suitability	-	
Wet Barefoot	-	
Material	Glazed Ceramic	
Classificiation	BIII	
CSV	VI	

Phys	ical Properties		
Test	/ Standard	Requirement	Test Result
	Length/Width EN ISO 10545-4	±0.5%≤ ± 2mm	±0.25%
+	Straightness of Sides EN ISO 10545-2	±0.3% ≤ ± 1.5mm	± 0.15%
-	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	± 0.4%
$\stackrel{\downarrow}{\hline\uparrow\uparrow}$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.2%
$\widehat{\ }_{\downarrow}^{\uparrow}$	Warpage EN ISO 10545-2	±0.5%≤ ± 2mm	0.30%
	Water Absorption EN ISO 10545-3	10% to 20%	15% to 17%
Ĺ	Modulus of Rupture EN ISO 10545-4	Ave 15N/mm²	25N/mm²
*	Frost Resistance Not Applicable	N/A	Not suitable
Å	Chemical Resistance EN ISO 10545-13	Min Class B	Class A-B (better)
	Stain Resistance EN ISO 10545-14	Min Class 3	Class 3 (better)
X	Crazing Resistance EN ISO 10545-11	Pass	Pass
	UV Colour Resistance		Unaffected by light
0	Scratch Hardness BS6431-Part 13/FN101	≥3	4

Available Sizes 150x150x8mm

Samples Service

Tel: +44 (0)1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0)1782 524 111 Fax: +44 (0) 1782 577 379 Email: techadvice@johnson-tiles.com BS6431:Part13/EN101

Fire Rating

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36 represents a low slip potential. All figures are accurate at the time of this data sheets creation (30/04/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.



Class A1 Non

Combustible

