ROMA PRODUCT DATA SHEET



Available Sizes
250x220x10mm (Hexagon)
660x660x10mm

· • • ·	Range	Roma
	Category	Stone, Speckle, Floor Tiles
	Collection	Select Collection
	Short Code	RMA02N
Alter Trees	Colour	Silver Grey
* *	Finish	Natural
	Wall Suitability	Internal & External
	Floor Suitability	Internal Only
	Wet Barefoot	-
	Material	Glazed Porcelain
	Classificiation	Bla
	Light Reflectance Value	56.00
	CSV	V2
	PTV (96)	Wet 0-24 Dry 36+
	PTV (55)	-
	R Value	9
	Wet Ramp	-
com	PEI	IV
	Traffic	Commercial

Up to 10%

Physical Properties				
Test /	Standard	Requirement	Test Result	
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass	
${{}}{}{}{}{}{}{}{}}{}{}{}{}{}{}{}{}{}{}{}{}{}{}{}{}{}}{}{}{}{}{}}{}{}{}}{}{}{}}{}{}{}{}}{}{}}{}{}{}{}}{}{}{}{}}{}{}}{}}{}{}{}{}{}$	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass	
- +	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass	
+	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
$\overset{\checkmark}{\overbrace{\land\uparrow\uparrow}}$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
	Water Absorption EN ISO 10545-3	≤0.5%	≤0.5%	
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥35N/mm²	
	Thermal Shock EN ISO 10545-9	Pass	Pass	
*	Frost Resistance EN ISO 10545-12	Resistant	Resistant	
B	Chemical Resistance EN ISO 10545-13	Min Class B	Class A	
	Stain Resistance EN ISO 10545-14	Min Class 3	Class 5	
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible	
kg	Weight/m² Thickness: 10mm		26.4kg	

Samples Service

Tel: +44 (0) | 782 524 043 Fax: +44 (0) | 782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | Fax: +44 (0) | 782 577 379 Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (01/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.

