SANCTUARY PRODUCT DATA SHEET





Available Sizes 300x200x8mm

| Up to 20% |
|------------------|
| Sanctuary |
| Stone, Marble |
| Intro Collection |
| MLOCKS |
| Matlock |
| Satin |
| Internal Only |
| - |
| - |
| Glazed Ceramic |
| BIII |
| 75.00 |
| VI |
| |

Samples Service

Tel: +44 (0) | 782 524 043 Fax: +44 (0) | 782 577 379

Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | | Fax: +44 (0) | 782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

| Physical Properties | | |
|---|-----------------|------------------------------|
| Test / Standard | Requirement | Test Result |
| Length/Width EN ISO 10545-2 | ±0.5%≤ ± 2mm | ±0.25% |
| Straightness of Sides EN ISO 10545-2 | ±0.3% ≤ ± 1.5mm | ± 0.15% |
| Rectangularity EN ISO 10545-2 | ±0.5% ≤ ± 2mm | ± 0.4% |
| Surface Flatness EN ISO 10545-2 | ±0.5% ≤ ± 2mm | ±0.2% |
| Warpage EN ISO 10545-2 | ±0.5%≤ ± 2mm | 0.30% |
| Water Absorption EN ISO 10545-3 | 10% to 20% | 15% to 17% |
| Modulus of Rupture EN ISO 10545-4 | Ave I5N/mm² | 25N/mm² |
| Frost Resistance Not Applicable | N/A | Not suitable |
| Chemical Resistance EN ISO 10545-13 | Min Class B | Class A-B (better) |
| Stain Resistance EN ISO 10545-14 | Min Class 3 | Class 3 (better) |
| Crazing Resistance EN ISO 10545-11 | Pass | Pass |
| UV Colour Resistance | | Unaffected by light |
| Scratch Hardness BS6431:Part13/EN101 | ≥3 | 4 |
| Fire Rating | | Class A I Non Combustible |
| kg Weight/m² Thickness: 8mm | | 14.1kg |



