SAVOY PRODUCT DATA SHEET



Available Sizes 200x200x8.5mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

$oldsymbol{arrho}$ Recycled Content	Up to 50%	
Range	Savoy	
Category	Concrete, Pattern, Floor	
	Tiles, PTV 36+ Tiles	
Collection	Select Collection	
Short Code	SAVFIS	
Colour	Grey Square Décor	
Finish	Natural	
Wall Suitability	Internal & External	
Floor Suitability	Internal Only	
Wet Barefoot	-	
Material	Glazed Porcelain	
Classificiation	Bla	
CSV	V2	
PTV (96)	Wet 36+ Dry 36+	
PTV (55)	-	
R Value	-	
Wet Ramp	-	
PEI	IV	
Traffic	Commercial	

Physical Properties			
Test /	Standard	Requirement	Test Result
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	±0.35%
$\boxed{\qquad}$	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	±1.5%
- +	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	±0.1%
	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.4%
$\left \begin{array}{c} \downarrow \\ \uparrow \uparrow \end{array}\right $	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
	Water Absorption EN ISO 10545-3	≤0.5%	≤0.1%
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥52N/mm²
	Thermal Shock EN ISO 10545-9	Pass	Pass
 ※	Frost Resistance EN ISO 10545-12	Resistant	Resistant
	Chemical Resistance EN ISO 10545-13	Min Class B	Pass
	Stain Resistance EN ISO 10545-14	Min Class 3	Class 5
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible
kg	Weight/m ² Thickness: 8.5mm		18.5kg

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, hadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate by potential and 364 represents a low slip potential. All figures are accurate at the time of this data sheets creation (13/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in Englanc No. 15/01/01/37, 20/205 | Johnson Tiles All rights reserved

