
# **SAVOY** PRODUCT DATA SHEET



${\cal O}$ Recycled Content	Up to 20%	
Range	Savoy	
Category	Colour	
Collection	Select Collection	
Short Code	SAV09A	
Colour	Sage	
Finish	Gloss	
Wall Suitability	Internal Only	
Floor Suitability	-	
Wet Barefoot	-	
Material	Glazed Ceramic	
Classificiation	BIII	
Light Reflectance Value	32.00	
CSV	V3	

Physical Properties		
Test / Standard	Requirement	Test Result
Length/Width EN ISO 10545-2	±0.5%≤ ± 2mm	±0.25%
Straightness of Sides EN ISO 10545-2	±0.3% ≤ ± 1.5mm	± 0.15%
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.4%
↓ Surface Flatness   ↑ ↑ EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.2%
→ Warpage ← EN ISO 10545-2	±0.5%≤ ± 2mm	0.30%
Water Absorption EN ISO 10545-3	10% to 20%	15% to 17%
Modulus of Rupture EN ISO 10545-4	Ave 15N/mm²	25N/mm²
Frost Resistance Not Applicable	N/A	Not suitable
Chemical Resistance EN ISO 10545-13	Min Class B	Class A-B (better)
Stain Resistance EN ISO 10545-14	Min Class 3	Class 3 (better)
Crazing Resistance EN ISO 10545-11	Pass	Pass
UV Colour Resistance		Unaffected by light
Fire Rating		Class A I Non Combustible
kg Thickness: 6.5mm Thickness: 8mm		11.7kg 14.1kg

## Available Sizes 300x100x8mm

### Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

#### Technical Helpline

Tel: +44 (0) | 782 524 | | | Fax: +44 (0) | 782 577 379 Email: techadvice@johnson-tiles.com

#### www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 – 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (01/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.

