

Select Collection - Boundary Earthtones Natural +



Available Sizes

Tile

600 x 600 x 20mm

Descriptive Colour	Earthtones
Finish	Natural +
Range	Boundary
Shortcode	BON01E
Suitabilities	<input checked="" type="checkbox"/> Internal & External <input checked="" type="checkbox"/> Internal & External
Material	Porcelain
Classification	B1a
Light Reflectance Value	18.00
NCS	6005-Y50R
Colour Shade Variation (CSV)	V2
PEI	III
Pendulum Dry 4S	36+
Pendulum Wet 4S	36+
TRL Wet Barefoot	36+
Traffic	Light Commercial

Physical properties

Test	Standard	Requirement	Typical test value
Length/Width	EN ISO 10545-2	$\pm 0.6\% \leq \pm 2\text{mm}$	Pass
Thickness	EN ISO 10545-2	$\pm 5\% \leq \pm 0.5\text{mm}$	Pass
Straightness of Sides	EN ISO 10545-2	$\pm 0.5\% \leq \pm 1.5\text{mm}$	< 0.2%
Rectangularity	EN ISO 10545-2	$\pm 0.6\% \leq \pm 2\text{mm}$	$\pm 0.2\%$
Water Absorption	EN ISO 10545-3	$\leq 0.5\%$	< 0.1%
Modulus of Rupture	EN ISO 10545-4	$\geq 1300\text{N}/\text{mm}^2$	$\geq 1300\text{N}/\text{mm}^2$
Thermal Shock	EN ISO 10545-9	Pass	Pass
Frost Resistance	EN ISO 10545-12	Resistant	Resistant
Chemical Resistance	EN ISO 10545-13	Min Class B	Class A
Stain Resistance	EN ISO 10545-14	Min Class 3	Class 5
Fire Rating	Not Applicable	N/A	Class A1FL Non Combustible
Weight/m ²			46.31kg
Thickness 20mm			

Samples

Tel: +44 (0) 1782 524043

Fax: +44 (0) 1782 577379

Email: samples@johnson-tiles.com

Technical helpline

Tel: +44 (0) 1782 524111

Fax: +44 (0) 1782 577379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

The colours shown on the tile products in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are correct at the time of testing and represent the standard production value. Please note: Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The Pendulum test results have been displayed in line with the Health and Safety Executive guidelines whereby 0-24 represents a high slip potential, 25-35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures accurate at time of data sheet creation (04/12/2020). Johnson Tiles is a division of Norcros Group (Holdings) Limited, Ladyfield House, Station Road, Wilmslow, Cheshire, SK9 1BU. Registered in England number 566694. Johnson Tiles, Johnson, Absolute and Material Lab are registered trademarks and together with Kerastar and the product names are the trademarks of H&R Johnson Tiles Limited and licensed to Norcros Group (Holdings) Limited, trading as Johnson Tiles. ©2013 Johnson Tiles. All rights reserved.