

Select Collection - Modern Moonstone Polished



Descriptive Colour	Moonstone
Finish	Polished
Range	Modern
Shortcode	MDN03P
Suitabilities	<input checked="" type="checkbox"/> Internal & External <input type="checkbox"/> Internal

Material	Un-glazed Porcelain
Classification	B1a
Light Reflectance Value	54.00
NCS	2005-Y40R
Colour Shade Variation (CSV)	V2
Pendulum Dry 4S	36+
Pendulum Wet 4S	0 - 24
Traffic	Commercial

Available Sizes

Tile
600 x 300 x 8mm
600 x 600 x 8mm

Physical properties

Test	Standard	Requirement	Typical test value
Length/Width	EN ISO 10545-2	$\pm 0.6\% \leq \pm 2\text{mm}$	$\pm 0.3\%$
Thickness	EN ISO 10545-2	$\pm 5\% \leq \pm 0.5\text{mm}$	$\pm 4\%$
Straightness of Sides	EN ISO 10545-2	$\pm 0.5\% \leq \pm 1.5\text{mm}$	$\pm 0.2\%$
Rectangularity	EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	$\pm 0.3\%$
Surface Flatness	EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	$\pm 0.3\%$
Water Absorption	EN ISO 10545-3	$\leq 0.5\%$	$< 0.2\%$
Modulus of Rupture	EN ISO 10545-4	$\geq 35\text{N/mm}^2$	$> 40\text{N/mm}^2$
Abrasion Resistance	EN ISO 10545-6		$< 140\text{mm}^3$
Thermal Shock	EN ISO 10545-9	Pass	Pass
Frost Resistance	EN ISO 10545-12	Resistant	Resistant
Chemical Resistance	EN ISO 10545-13	Min Class B	Class A
Stain Resistance	EN ISO 10545-14	Min Class 3	$> \text{Class 3}$
Fire Rating	Not Applicable	N/A	Class A IFL Non Combustible
Weight/m ²			18.2kg 20.2kg
Thickness: 8mm			
Thickness: 9mm			
UV Colour Resistance			Unaffected by light

Samples
 Tel: +44 (0) 1782 524043
 Fax: +44 (0) 1782 577379
 Email: samples@johnson-tiles.com

Technical helpline
 Tel: +44 (0) 1782 524111
 Fax: +44 (0) 1782 577379
 Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

The colours shown on the tile products in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are correct at the time of testing and represent the standard production value. Please note: Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The Pendulum test results have been displayed in line with the Health and Safety Executive guidelines whereby 0-24 represents a high slip potential, 25-35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures accurate at time of data sheet creation (04/12/2020). Johnson Tiles is a division of Norcros Group (Holdings) Limited, Ladyfield House, Station Road, Wilmslow, Cheshire, SK9 1BU. Registered in England number 566694. Johnson Tiles, Johnson, Absolute and Material Lab are registered trademarks and together with Kerastar and the product names are the trademarks of H&R *Johnson Tiles Limited and licensed to Norcros Group (Holdings) Limited, trading as Johnson Tiles. ©2013 Johnson Tiles. All rights reserved.