SLOAN PRODUCT DATA SHEET



	Range	Sloan		-	al Prope
	Category	Stone, Floor Tiles	-	Test /	Standar
A REAL	Collection	Absolute Collection	-		Length EN ISO
	Short Code	SLN02P		$\stackrel{\flat}{\sqsubseteq}$	Thickne EN ISO
and the second	Colour	Hazelwood	-	-[]+	Straigh
	Finish	Polished	-		EN ISO
	Wall Suitability	Internal & External	-		Rectan EN ISO
	Floor Suitability	Internal Only		$[] \downarrow] \uparrow \uparrow$	Surface EN ISO
	Wet Barefoot	-	-	\land	Water
	Material	Un-glazed Porcelain	-		EN ISO
	Classificiation	Bla	-		Modulu EN ISO
	Light Reflectance Value	42.00		Mr.	Therma EN ISO
	CSV	V2	-		Frost R
	PTV (96)	Wet 0-24 Dry 36+	-	*	ENISO
	PTV (55)	-	_	Å	Chemic EN ISO
	R Value	-	-	A	Stain R
	Wet Ramp	-	-		EN ISO
	PEI	-	-		Fire Rat Not App
	Traffic	Commercial	_	kg	Weight Thickne

Physical Properties					
Test / Standard		Requirement	Test Result		
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass		
$\rightarrow]] \leftarrow$	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass		
+	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass		
-	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass		
${\rightarrow} ^{\uparrow}$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass		
	Water Absorption EN ISO 10545-3	≤0.5%	≤0.1%		
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥45N/mm²		
	Thermal Shock EN ISO 10545-9	Pass	Pass		
*	Frost Resistance EN ISO 10545-12	Resistant	Resistant		
ð	Chemical Resistance EN ISO 10545-13	Min Class B	Min Class B		
	Stain Resistance EN ISO 10545-14	Min Class 3	Min Class 3		
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible		
kg	Weight/m² Thickness: 10.5mm		25.25kg		

Physical Properties

Samples Service

Available Sizes 600x300x10.5mm 600x600x10.5mm 1200x1200x10.5mm 1200x600x10.5mm

Tel: +44 (0)1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0)1782 524 111 Fax: +44 (0) 1782 577 379 Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction i the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potentia and 36 represents a low slip potential. All figures are accurate at the time of this data sheets creation (17/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in Engla No. 15600432. © 2025 Johnson Tiles. All rights reserved.



