## **SLOAN** PRODUCT DATA SHEET

	Range	Sloan	
	Category	Stone, Mosaic, Floor Tiles	
	Collection	Absolute Collection	
	Short Code	SLN7NM	
	Colour	Lead	
	Finish	Natural - Square Mosaic	
-	Wall Suitability	Internal & External	
	Floor Suitability	Internal Only	
	Wet Barefoot	-	
	Material	Un-glazed Porcelain	
	Classificiation	Bla	
	Light Reflectance Value	15.00	
	CSV	V2	
	PTV (96)	Wet 0-24 Dry 36+	
	PTV (55)	-	
	R Value	10	
	Wet Ramp	Α	
	PEI	-	
	Traffic	Commercial	

Physical Properties					
Test /	Standard	Requirement	Test Result		
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass		
$\overset{\checkmark}{\frown}$	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass		
-	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass		
-	<b>Rectangularity</b> EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass		
$\stackrel{\checkmark}{ \uparrow \uparrow}$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass		
	Water Absorption EN ISO 10545-3	≤0.5%	≤0.1%		
	<b>Modulus of Rupture</b> EN ISO 10545-4	≥35N/mm²	≥45N/mm²		
	Thermal Shock EN ISO 10545-9	Pass	Pass		
*	Frost Resistance EN ISO 10545-12	Resistant	Resistant		
Æ	Chemical Resistance EN ISO 10545-13	Min Class B	Min Class B		
	Stain Resistance EN ISO 10545-14	Min Class 3	Min Class 3		
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible		
kg	<b>Weight/m²</b> Thickness: 10.5mm		25.25kg		

## Samples Service

**Available Sizes** 

300x300x10.5mm (33x33mm)

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

## Technical Helpline

Tel: +44 (0) | 782 524 | | | Fax: +44 (0) | 782 577 379 Email: techadvice@johnson-tiles.com

## www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (09/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.

