SLOAN PRODUCT DATA SHEET



19.16		,,,
		Tiles
	Collection	Absolute Collection
	Short Code	SLN06B
	Colour	Smoke
	Finish	Bush Hammered
	Wall Suitability	Internal & External
	Floor Suitability	Internal & External
	Wet Barefoot	Yes
	Material	Un-glazed Porcelain
	Classificiation	Bla
	Light Reflectance Value	29.00
	CSV	V2
	PTV (96)	Wet 36+ Dry 36+
	PTV (55)	Wet 36+
	R Value	11
	Wet Ramp	c
	PEI	-
	Traffic	Commercial

Range

Category

Sloan

Stone, Floor Tiles, PTV 36+

Physical Properties			
Fest / Standard	Requirement	Test Result	
Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass	
	±5%≤ ± 0.5mm	Pass	
Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass	
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
◆ ↑ ↑ Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
Water Absorption EN ISO 10545-3	≤0.5%	≤0.1%	
Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥45N/mm²	
Thermal Shock EN ISO 10545-9	Pass	Pass	
Frost Resistance EN ISO 10545-12	Resistant	Resistant	
Chemical Resistance EN ISO 10545-13	Min Class B	Min Class B	
Stain Resistance EN ISO 10545-14	Min Class 3	Min Class 3	
Fire Rating Not Applicable	N/A	Class A I FL Non Combustible	
kg Weight/m ² Thickness: 10.5mm		25.25kg	

Samples Service

Available Sizes 600x600x10.5mm 600x300x10.5mm

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | Fax: +44 (0) | 782 577 379 Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (01/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.



