## **SLOAN** PRODUCT DATA SHEET

	1		

Range	Sloan		
Category	Stone, Mosaic, Floor Tiles		
Collection	Absolute Collection		
Short Code	SLN6NM		
Colour	Smoke		
Finish	Natural - Square Mosaic		
Wall Suitability	Internal & External		
Floor Suitability	Internal Only		
Wet Barefoot	-		
Material	Un-glazed Porcelain		
Classificiation	Bla		
Light Reflectance Value	29.00		
CSV	V2		
PTV (96)	Wet 0-24 Dry 36+		
PTV (55)	-		
R Value	10		
Wet Ramp	Α		
PEI	-		
Traffic	Commercial		

Physical Properties						
Test / Standard		Requirement	Test Result			
Length/Widt EN ISO 1054		±0.6%≤ ± 2mm	Pass			
Thickness Thickness EN ISO 1054	5-2	±5%≤ ± 0.5mm	Pass			
Straightness EN ISO 1054		±0.5% ≤ ± 1.5mm	Pass			
Rectangular EN ISO 1054	•	±0.5% ≤ ± 2mm	Pass			
→ Surface Flat ↑↑ EN ISO 1054		±0.5% ≤ ± 2mm	Pass			
Water Absor EN ISO 1054	•	≤0.5%	≤0.1%			
Modulus of I EN ISO 1054		≥35N/mm²	≥45N/mm²			
Thermal Sho EN ISO 1054		Pass	Pass			
Frost Resista EN ISO 1054		Resistant	Resistant			
Chemical Re EN ISO 1054		Min Class B	Min Class B			
Stain Resista EN ISO 1054		Min Class 3	Min Class 3			
Fire Rating Not Applicab	le	N/A	Class A I FL Non Combustible			
kg Weight/m <sup>2</sup> Thickness: 10	).5mm		25.25kg			

## Samples Service

**Available Sizes** 

300x300x10.5mm (33x33mm)

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

## Technical Helpline

Tel: +44 (0) | 782 524 | | | Fax: +44 (0) | 782 577 379 Email: techadvice@johnson-tiles.com

## www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (09/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.

