## **STAMFORD** PRODUCT DATA SHEET





## **Available Sizes**

600x600x10mm 1200x1200x9mm 1200x600x10.5mm 600x300x10mm

## Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

## Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

arrho Recycled Content	Up to 40%	
Range	Stamford	
Category	Concrete, Floor Tiles, PTV	
	36+ Tiles	
Collection	Absolute Collection	
Short Code	SMF04N	
Colour	Charcoal	
Finish	Natural	
Wall Suitability	Internal & External	
Floor Suitability	Internal Only	
Wet Barefoot	-	
Material	Glazed Porcelain	
Classificiation	Bla	
Light Reflectance Value	19.00	
CSV	V2	
PTV (96)	Wet 36+ Dry 36+	
PTV (55)	-	
R Value	10	
Wet Ramp	С	
PEI	III	
Traffic	Light Commercial	

Physical Properties		
Test / Standard	Requirement	Test Result
Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	±0.1%
Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	±0.5%
Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	±0.22%
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.22%
Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.22%
Water Absorption EN ISO 10545-3	≤0.5%	Pass
Modulus of Rupture EN ISO 10545-4	≥35N/mm²	Pass
Thermal Shock EN ISO 10545-9	Pass	Pass
Frost Resistance EN ISO 10545-12	Resistant	Resistant
Chemical Resistance EN ISO 10545-13	Min Class B	Class B
Stain Resistance EN ISO 10545-14	Min Class 3	Pass
UV Colour Resistance		Unaffected by light
Fire Rating Not Applicable	N/A	Class A1FL Non Combustible
Weight/m² Thickness:9mm Thickness:10mm Thickness:10.5mm		21.06kg 22.5kg 22.33kg 24.66kg

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential. All figures are accurate at the time of this data sheets creation (17/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in Englan No. 15600432. © 2025 Johnson Tiles. All rights reserved.

