TERRAZZO PRODUCT DATA SHEET





Available Sizes

600x600x9.2mm 1200x600x9.2mm 1600x800x9.8mm 800x800x9.8mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | | Fax: +44 (0) | 782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Ø Recycled Content	Up to 40%	
Range	Terrazzo	
Category	Stone, Speckle, Floor Tile	
Collection	Select Collection	
Short Code	TRZOIN	
Colour	Light Stone	
Finish	Natural	
Wall Suitability	Internal & External	
Floor Suitability	Internal Only	
Wet Barefoot	-	
Material	Glazed Porcelain	
Classificiation	Bla	
Light Reflectance Value	38.00	
CSV	V2	
PTV (96)	Wet 25-35 Dry 36+	
PTV (55)	-	
R Value	10	
Wet Ramp	-	
PEI	IV	
Traffic	Commercial	

Physical Properties		
Test / Standard	Requirement	Test Result
Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	±0.1%
Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	±2.1%
Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	±0.1%
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.1%
Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.2%
Water Absorption EN ISO 10545-3	≤0.5%	≤0.1%
Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥37N/mm²
Thermal Shock EN ISO 10545-9	Pass	Pass
Frost Resistance EN ISO 10545-12	Resistant	Resistant
Chemical Resistance EN ISO 10545-13	Min Class B	Class A
Stain Resistance EN ISO 10545-14	Min Class 3	Class 5
Fire Rating Not Applicable	N/A	Class A I FL Non Combustible
kg Weight/m² Thickness: 9.5mm		19kg

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small varies resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant processor as the slip resistance of some produlum test results are displayed in line with The Health & Safety Executive guidalines whereby 0.24 represents a bind sign potential 25 x 35 significant moderates.

