TUNDRA PRODUCT DATA SHEET



-1		

${oldsymbol{arrho}}$ Recycled Content	Up to 20%	
Range	Tundra	
Category	White, Made in the UK	
Collection	Intro Collection	
Short Code	TUND2A	
Colour	White	
Finish	Matt	
Wall Suitability	Internal Only	
Floor Suitability	-	
Wet Barefoot	-	
Material	Glazed Ceramic	
Classificiation	BIII	
Light Reflectance Value	81.00	
CSV	VI	

Available Sizes 360x275x8mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379

Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Physical Properties					
Test / Standard	Requirement	Test Result			
Length/Width EN ISO 10545-2	±0.5%≤ ± 2mm	±0.25%			
Straightness of Sides EN ISO 10545-2	±0.3% ≤ ± 1.5mm	± 0.15%			
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.4%			
Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.2%			
Warpage EN ISO 10545-2	±0.5%≤ ± 2mm	0.30%			
Water Absorption EN ISO 10545-3	10% to 20%	15% to 17%			
Modulus of Rupture EN ISO 10545-4	Ave I5N/mm²	25N/mm²			
Frost Resistance Not Applicable	N/A	Not suitable			
Chemical Resistance EN ISO 10545-13	Min Class B	Class A-B (better)			
Stain Resistance EN ISO 10545-14	Min Class 3	Class 3 (better)			
Crazing Resistance EN ISO 10545-11	Pass	Pass			
UV Colour Resistance		Unaffected by light			
Scratch Hardness BS6431:Part13/EN101	≥3	4			
Fire Rating		Class A1 Non Combustible			
kg Weight/m² Thickness: 8mm		14.1kg			

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (21/03/201). Johnson Tiles is a division of Norcros Group (Holdings) Limited, Ladyfield House, Station Road, Wilmslow, Cheshire, SK9 1BU. Registed in England No. 566694. Johnson Tiles, Johnson, Absolute and Material Lab are registered trademarks and together with Kerastar and product names are the trademarks of H&R Johnson Tiles. Emitted and licensed to Norcros Group (Holdings) Limited trading as Johnson Tiles. © 2021 Johnson Tiles. All rights reserved.

