
## **VERSO** PRODUCT DATA SHEET



	wate Suitability	internat d Exte
	Floor Suitability	Internal Only
Available Sizes	Wet Barefoot	-
370x92x9mm	Material	Glazed Porcela
	Classificiation	Bla
	Light Reflectance Value	34.00
	CSV	V2
	PTV (96)	Wet 36+ Dry 3
Samples Service	PTV (55)	-
Tel: +44 (0)1782 524 043 Fax: +44 (0)1782 577 379	R Value	-
Email: samples@johnson-tiles.com	Wet Ramp	-
Technical Helpline Tel: +44 (0)1782 524 111	PEI	IV
Fax: +44 (0) 1782 577 379 Email: techadvice@johnson-tiles.com	Traffic	Commercial
Email. techadvice@jonnson=tites.com		

${\cal O}$ Recycled Content	Up to 50%
Range	Verso
Category	Colour, Floor Tiles, PTV
	36+ Tiles
Collection	Absolute Collection
Short Code	VRS07N
Colour	Biscuit
Finish	Natural
Wall Suitability	Internal & External
Floor Suitability	Internal Only
Wet Barefoot	-
Material	Glazed Porcelain
Classificiation	Bla
Light Reflectance Value	34.00
CSV	V2
PTV (96)	Wet 36+ Dry 36+
PTV (55)	-
R Value	-
Wet Ramp	-
PEI	IV
Traffic	Commercial

Physical Properties			
Test / Standard	Requirement	Test Result	
Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass	
Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass	
Straightness of Side EN ISO 10545-2	<b>des</b> ±0.5% ≤ ± 1.5mm	Pass	
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
Water Absorption EN ISO 10545-3	≤0.5%	≤0.5%	
Modulus of Ruptu EN ISO 10545-4	ire ≥35N/mm²	≥35N/mm²	
Thermal Shock EN ISO 10545-9	Pass	Pass	
Frost Resistance EN ISO 10545-12	Resistant	Resistant	
Chemical Resistan EN ISO 10545-13	nce Min Class B	Class A	
Stain Resistance EN ISO 10545-14	Min Class 3	Class 5	
Fire Rating Not Applicable	N/A	Class A I FL Non Combustible	
kg Weight/m <sup>2</sup> Thickness: 9mm		20.1 kg	

## www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (01/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.



