VERSO PRODUCT DATA SHEET





Available Sizes 370x92x9mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379

Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | | Fax: +44 (0) | 782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Ø Recycled Content ø Recycled Content ø Recycled Content ø Recycled Content	Up to 50%	
Range	Verso	
Category	Colour, Floor Tiles, PTV	
	36+ Tiles	
Collection	Absolute Collection	
Short Code	VRSIIN	
Colour	Blue	
Finish	Natural	
Wall Suitability	Internal & External	
Floor Suitability	Internal Only	
Wet Barefoot	-	
Material	Glazed Porcelain	
Classificiation	Bla	
Light Reflectance Value	15.00	
CSV	V2	
PTV (96)	Wet 36+ Dry 36+	
PTV (55)	-	
R Value	-	
Wet Ramp	-	
PEI	IV	
Traffic	Commercial	

Physical Properties				
Test /	Standard	Requirement	Test Result	
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass	
$\begin{array}{ c c }\hline \downarrow \\ \hline \uparrow \\ \hline \end{array}$	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass	
+	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass	
-	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
$\stackrel{\checkmark}{\uparrow} \uparrow$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
	Water Absorption EN ISO 10545-3	≤0.5%	≤0.5%	
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥35N/mm²	
	Thermal Shock EN ISO 10545-9	Pass	Pass	
濼	Frost Resistance EN ISO 10545-12	Resistant	Resistant	
	Chemical Resistance EN ISO 10545-13	Min Class B	Class A	
	Stain Resistance EN ISO 10545-14	Min Class 3	Class 5	
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible	
kg	Weight/m² Thickness: 9mm		20.1 kg	

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (01/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.

