
VIVID PRODUCT DATA SHEET



| ${\mathscr O}$ Recycled Content | Up to 20% |
|---------------------------------|------------------------|
| | |
| Range | Vivid |
| Category | Colour, Made in the UK |
| Collection | Select Collection |
| Short Code | VVD7A |
| Colour | Lime |
| Finish | Gloss |
| Wall Suitability | Internal Only |
| Floor Suitability | - |
| Wet Barefoot | - |
| Material | Glazed Ceramic |
| Classificiation | BIII |
| Light Reflectance Value | 8.00 |
| CSV | VI |

| Physical Properties | | |
|---|-------------------------|------------------------------|
| Test / Standard | Requirement | Test Result |
| Length/Width EN ISO 10545-2 | ±0.5%≤ ± 2mm | ±0.25% |
| Straightness of Sides EN ISO 10545-2 | ±0.3% ≤ ± 1.5mm | ± 0.15% |
| Rectangularity EN ISO 10545-2 | ±0.5% ≤ ± 2mm | ±0.4% |
| ↓ Surface Flatness ↑ ↑ EN ISO 10545-2 | ±0.5% ≤ ± 2mm | ±0.2% |
| → Warpage ← EN ISO 10545-2 | ±0.5%≤ ± 2mm | 0.30% |
| Water Absorption EN ISO 10545-3 | 10% to 20% | 15% to 17% |
| Modulus of Rupture EN ISO 10545-4 | Ave 15N/mm ² | 25N/mm² |
| Frost Resistance Not Applicable | N/A | Not suitable |
| Chemical Resistance EN ISO 10545-13 | Min Class B | Class A-B (better) |
| Stain Resistance EN ISO 10545-14 | Min Class 3 | Class 3 (better) |
| Crazing Resistance EN ISO 10545-11 | Pass | Pass |
| UV Colour Resistance | | Unaffected by light |
| Scratch Hardness BS6431:Part13/EN101 | ≥3 | 4 |
| Fire Rating | | Class A I Non Combustible |
| kg Weight/m ² Thickness: 10mm | | 17kg |

Available Sizes

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | Fax: +44 (0) | 782 577 379 Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a line bilp potential. 25 - 35 significas a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (21/03/2021). Johnson Tiles is a division of Norcros Group (Holdings) Limited, Ladyfield House, Station Road, Wilmslow, Cheshire, SK91 BU. Registed in England No. 566694. Johnson Tiles, Johnson Tiles. All rights reserved.



