## **ZEYA PRODUCT DATA SHEET**





## **Available Sizes**

450x450x8.5mm 600x300x8.7mm 745x745x9.7mm 995x995x10mm 1200x595x10mm 600x600x9.5mm

## Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

## Technical Helpline

Tel: +44 (0) | 782 524 | | | | Fax: +44 (0) | 782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Range	Zeya	
Category	Stone, Floor Tiles	
Collection	Select Collection	
Short Code	ZEYOIN	
Colour	Chalk	
Finish	Natural	
Wall Suitability	Internal & External	
Floor Suitability	Internal Only	
Wet Barefoot	-	
Material	Glazed Porcelain	
Classificiation	Bla	
Light Reflectance Value	54.00	
CSV	V3	
PTV (96)	Wet 25-35 Dry 36+	
PTV (55)	-	
R Value	-	
Wet Ramp	-	
PEI	IV	
Traffic	Commercial	

Physical Properties				
Test	/ Standard	Requirement	Test Result	
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass	
	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass	
	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass	
	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
$\begin{array}{ c c }\hline \downarrow \\\hline \uparrow \uparrow \end{array}$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
	Water Absorption EN ISO 10545-3	≤0.5%	≤0.5%	
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥35N/mm²	
	Thermal Shock EN ISO 10545-9	Pass	Pass	
*	Frost Resistance EN ISO 10545-12	Resistant	Resistant	
	Chemical Resistance EN ISO 10545-13	Min Class B	Min Class B	
	Stain Resistance EN ISO 10545-14	Min Class 3	Min Class 3	
\$uv\$	UV Colour Resistance		Unaffected by light	
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible	
kg	Weight/m <sup>2</sup>		(7.0)	
	Thickness: 8.5mm Thickness: 8.7mm		17.8kg 18.2kg	
	Thickness: 6.7mm		10.2kg 20.25kg	
	Thickness: 9.7mm		19.63kg	
	Thickness: 10mm		22.3kg	
	Thickness: 20mm		38.2kg	
	small variations in slip		Est. 1901	

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential, and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (30/04/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in Englar No. 1550/04/2025 by the properties of the production o

