ZEYA PRODUCT DATA SHEET





Available Sizes

450x450x8.5mm 600x300x8.7mm 745x745x9.7mm 995x995x10mm 1200x595x10mm 600x600x9.5mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | | Fax: +44 (0) | 782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Range	Zeya	
Category	Stone, Floor Tiles	
Collection	Select Collection	
Short Code	ZEY04N	
Colour	Dark Grey	
Finish	Natural	
Wall Suitability	Internal & External	
Floor Suitability	Internal Only	
Wet Barefoot	-	
Material	Glazed Porcelain	
Classificiation	Bla	
Light Reflectance Value	32.00	
CSV	V3	
PTV (96)	Wet 25-35 Dry 36+	
PTV (55)	-	
R Value	-	
Wet Ramp	-	
PEI	III	
Traffic	Light Commercial	

Physical Properties			
Test / Standard	R	equirement	Test Result
Length/Widtl EN ISO 10545	+	0.6%≤ ± 2mm	Pass
Thickness EN ISO 10545	-2 ±	5%≤ ± 0.5mm	Pass
Straightness EN ISO 10545	+	0.5% ≤ ± 1.5mm	Pass
Rectangularit EN ISO 10545	. +	0.5% ≤ ± 2mm	Pass
Surface Flatn FN ISO 10545	+	0.5% ≤ ± 2mm	Pass
Water Absorp	<	0.5%	≤0.5%
Modulus of R EN ISO 10545	, ,	35N/mm²	≥35N/mm²
Thermal Shoo EN ISO 10545	P:	ass	Pass
Frost Resistar EN ISO 10545	R	esistant	Resistant
Chemical Res EN ISO 10545	M	lin Class B	Min Class B
Stain Resistar EN ISO 10545	Μ	lin Class 3	Min Class 3
UV Colour Re	sistance		Unaffected by light
Fire Rating Not Applicabl	e N	I/A	Class A I FL Non Combustible
Weight/m² Thickness: 8.5 Thickness: 8.7 Thickness: 9.5 Thickness: 9.7 Thickness: 10r	mm mm mm nm		17.8kg 18.2kg 20.25kg 19.63kg 22.3kg
Thickness: 20r	nm		38.2kg

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential. All figures are accurate at the time of this data sheets creation (01/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in Englan No. 15600432. © 2025 Johnson Tiles. All rights reserved.

