
ZEYA PRODUCT DATA SHEET





Available Sizes 745x745x9.7mm 1200x595x10mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Range	Zeya	
	•	
Category	Stone, Floor Tiles, PTV 36+	
	Tiles	
Collection	Select Collection	
Short Code	ZEY03G	
Colour	Taupe	
Finish	Grip	
Wall Suitability	Internal & External	
Floor Suitability	Internal & External	
Wet Barefoot	Yes	
Material	Glazed Porcelain	
Classificiation	Bla	
Light Reflectance Value	41.00	
CSV	V3	
PTV (4S)	Wet 36+ Dry 36+	
PTV (TRL)	Wet 36+	
R Value	-	
Wet Ramp	-	
PEI	III	
Traffic	Light Commercial	

Physical Properties			
Test /	Standard	Requirement	Test Result
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass
<u>↓</u>	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass
-]+	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass
-	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
$\begin{array}{ c c }\hline \downarrow \\\hline \uparrow \uparrow \\\hline \end{array}$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
	Water Absorption EN ISO 10545-3	≤0.5%	≤0.5%
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥35N/mm²
	Thermal Shock EN ISO 10545-9	Pass	Pass
<u>*</u>	Frost Resistance EN ISO 10545-12	Resistant	Resistant
	Chemical Resistance EN ISO 10545-13	Min Class B	Min Class B
	Stain Resistance EN ISO 10545-14	Min Class 3	Min Class 3
\$\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\	UV Colour Resistance		Unaffected by light
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible
kg	Weight/m ² Thickness: 8.5mm Thickness: 8.7mm Thickness: 9.5mm Thickness: 9.7mm Thickness: 1.0mm		17.8kg 18.2kg 20.25kg 19.63kg 22.3kg
	Thickness: 20mm		38.2kg

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (2 1/03/2021). Johnson Tiles is a division of Norcros Group (Holdings) Limited, Ladyfield House, Station Road, Wilmslow, Cheshire, SK9 IBU. Registed in England No. 566694. Johnson Tiles. Johnson, Absolute and Material Lab are registered trademarks and together with Kerastar and product names are the trademarks of H& Johnson Tiles Limited and licensed to Norcros Group (Holdings) Limited trading as Johnson Tiles. © 2021 Johnson Tiles. All rights reserved.

