## **ZION PRODUCT DATA SHEET**





## **Available Sizes** 600x600x8.5mm 600x300x8.5mm

## Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

## Technical Helpline

Tel: +44 (0) | 782 524 | | | | Fax: +44 (0) | 782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Range	Zion	
Category	Stone, Floor Tiles	
Collection	Select Collection	
Short Code	ZIN04P	
Colour	Basalt	
Finish	Polished	
Wall Suitability	Internal & External	
Floor Suitability	Internal Only	
Wet Barefoot	-	
Material	Un-glazed Porcelain	
Classificiation	Bla	
Light Reflectance Value	13.00	
CSV	V2	
PTV (96)	Wet 0-24 Dry 36+	
PTV (55)	-	
R Value	-	
Wet Ramp	-	
PEI	-	
Traffic	Commercial	

Physical Properties		
Test / Standard	Requirement	Test Result
Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	±0.1%
Thickness EN ISO I 0545-2	±5%≤ ± 0.5mm	±4%
Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	±0.1%
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.25%
Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.25%
Water Absorption EN ISO I 0545-3	≤0.5%	≤0.1%
Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥40N/mm²
Thermal Shock EN ISO 10545-9	Pass	Pass
Frost Resistance EN ISO 10545-12	Resistant	Resistant
Chemical Resistance EN ISO 10545-13	Min Class B	Class A
Stain Resistance EN ISO 10545-14	Min Class 3	Class 5
UV Colour Resistance		Unaffected by light
Fire Rating Not Applicable	N/A	Class A I FL Non Combustible
Weight/m² Thickness:8.5mm Thickness:9.2mm		21.19kg 21.88kg

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, lnadequate cleaning and maintenance of slip like at the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a liph slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (01/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5 JZ. Registered in England No. 156/0437 @ 2025 S. Dohnson Tiles Limited.

