## **ZION PRODUCT DATA SHEET**



A CONTRACTOR OF THE	Collection	Select Collection
	Short Code	ZIN02N
a start and a start of the star	Colour	Pebble
	Finish	Natural
and the second	Wall Suitability	Internal & Extern
	Floor Suitability	Internal Only
	Wet Barefoot	-
	Material	Un-glazed Porcel
ailable Sizes 0x600x9.2mm	Classificiation	Bla
	Light Reflectance Value	40.00
	CSV	V2
	PTV (96)	Wet 36+ Dry 36+
	PTV (55)	-
nples Service	R Value	10
	Wet Ramp	-
κ: +44 (0) l 782 577 379 nail: samples@johnson-tiles.com	PEI	-
	Traffic	Commercial
nnson-tiles.com		

Zion	-	ical Properties		
Stone, Floor Tiles, PTV 36+	Test	/ Standard	Requirement	Test Result
Tiles		<b>Length/Width</b> EN ISO 10545-2	±0.6%≤ ± 2mm	±0.1%
Select Collection	→ ↑	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	±4%
ZIN02N	П	Straightness of Sides		
Pebble	- +	EN ISO 10545-2	±0.5% ≤ ± 1.5mm	±0.1%
Natural	+	<b>Rectangularity</b> EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.25%
Internal & External	$[] \downarrow ] \uparrow \uparrow$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.25%
Internal Only				
-		Water Absorption EN ISO 10545-3	≤0.5%	≤0.1%
Un-glazed Porcelain		Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥40N/mm²
Bla	No.	Thermal Shock EN ISO 10545-9	Pass	Pass
40.00		EIN 150 10545-9		
V2	*	Frost Resistance EN ISO 10545-12	Resistant	Resistant
Wet 36+ Dry 36+	B	<b>Chemical Resistance</b> EN ISO 10545-13	Min Class B	Class A
-		Stain Resistance		
10		EN ISO 10545-14	Min Class 3	Class 5
-		UV Colour Resistance		Unaffected by light
-		<b>Fire Rating</b> Not Applicable	N/A	Class A I FL Non Combustible
Commercial		Weight/m <sup>2</sup>		
	kg	Thickness:8.5mm		21.19kg
		Thickness:9.2mm		21.17kg 21.88kg
				6

## Fax:

## Tec

## www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be smally variations in tip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential. 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All rights reserved. No. 15600452. © 2025 Johnson Tiles. All rights reserved.

Range

Category



