POLAR

GLAZED CERAMIC | WALL TILES

PLAIN COLOUR TILES INTRO











POLAR

Our Polar range is perfect for adding a sense of tranquillity to any interior. Reflecting light, this range can make a room feel clean, serene, and refreshingly simple. Polar offers a variety of finishes to add texture to any design scheme. Bumpy Gloss showcases a dappled effect, Gloss Wave emulates the natural movement of water, and Satin Linear Structured offers a fragmented, linear look.

Front Cover Image: White Satin 300x200mm - CLASIA & White Linear Structure Satin 300x200mm - CLASIL



VI: Low Shade Variation



WHITE


G PRGI + S PRSI2 LRV: 86

WHITE BUMPY

G ALPNIA LRV: 86



Sizes, Finishes & Availability



#	Size	Finish	Colour Availability	Thickness	Pieces/Box	Coverage/Box	Weight/Box
I	300x200mm	G Gloss	White & White Bumpy	8mm	17 Tiles	1.02 m²	I 4.00 kg
		S Satin	White	8mm	17 Tiles	1.02 m²	I 4.00 kg
2	300x200mm Scored I Way	G Gloss	White	8mm	15 Tiles	0.90 m²	I 4.70 kg
		S Satin	White	8mm	I 5 Tiles	0.90 m²	I 4.70 kg
3	300x200mm Scored 2 Ways	G Gloss	White	8mm	15 Tiles	0.90 m²	14.70 kg
4	300x200mm Wave Structure	G Gloss	White	8mm	17 Tiles	1.02 m²	14.00 kg
5	300x200mm Linear Structure	S Satin	White	8mm	17 Tiles	1.02 m²	14.00 kg
6	200x200mm	G Gloss	White Bumpy	6.5mm	25 Tiles	1.00 m²	I I.50 kg

Note: All sizes indicated are metric modular. All dimensions are in millimetres. All sizes shown are nominal. For the most up-to-date availability information, please visit our website. All LRV results are from Johnson Tiles' internal test reports and are to be used for guidance only. LRV: Light Reflectance Value.





Technical Data

Specification

Range	Size	Wall Suitability	Floor Suitability	Wet Barefoot	CSV	Material
Polar	All Sizes Shown	Internal Only	-	-	VI	Glazed Ceramic [BIII]

Physical Properties

Test/Standard	Requirement	Test Result	Test/Standard	Requirement	Test Result
Length / Width EN ISO I 0545 - 2	± 0.5% ≤ ± 2mm	≤ ± 0.25%	Modulus of Rupture EN ISO 10545 - 4	Min. I5N / mm²	≥ 25N / mm²
Thickness EN ISO I 0545 − 2	± 10% ≤ ± 0.5mm	± 2.5%	Thermal Shock EN ISO 10545 - 9	Pass	Pass
Straightness of Side EN ISO 10545 - 2	± 0.3% ≤ ± 1.5mm	± 0.15%	Frost Resistance EN ISO 10545 - 12	-	Not Suitable
Rectangularity EN ISO 0545 - 2	± 0.5% ≤ ± 2mm	± 0.4%	Chemical Resistance EN ISO 10545 - 13	Min. Class B	Class A - B
Surface Flatness EN ISO I 0545 - 2	± 0.5% ≤ ± 2mm	± 0.3%	Stain Resistance EN ISO 10545 - 14	Min. Class 3	Class 3
Water Absorption EN ISO I 0545 - 3	10% to 20%	15% to 17%	Fire Rating	-	Class A I Non Combustible
kg Weight / M²	I 4.I 0 kg 8mm thick	I I.50 kg 6.5mm thick			

Note: All products are classed as BIII - Glazed Ceramic. All products conform to BS EN 14411.

Range	Material	Recycled Content of the Tiles	Recycled Content of the Packaging	Recyclable Content of the Packaging	EPD
Polar	Glazed Ceramic [BIII]	Up to 20%	Up to 100%	Up to 100%	Yes

Important Information

During the manufacturing process of ceramic, vitrified and porcelain tiles, some variation in shade and pattern can occur. Before fixing any tiles; several boxes should be opened and their contents mixed to ensure that size, colour, shade and patterning are acceptable. The tiles shown are quality products and conform to the physical properties listed below.

- All sizes shown are metric modular.
- For specific suitability and fit-for-purpose details please contact our technical helpline.
- \bullet Johnson Tiles cannot accept responsibility for any tiles that have been fixed.
- \bullet Every effort has been made to ensure the accuracy of the information given.
- Johnson Tiles reserves the right to change specifications and availability without prior notice.
- Nothing in these statements does or will affect the statutory rights of the consumer.

® Johnson Tiles, Johnson, Absolute and Material Lab are registered trademarks and together with Kerastar and product names are the trademarks of H&R Johnson Tiles Limited and licensed to Norcros Group (Holdings) Limited trading as Johnson Tiles. © 2021 Johnson Tiles. All rights reserved.







For more information about Polar or any of our other product ranges simply visit www.johnson-tiles.com | f ♥ ◎ P in ▶

Where To Find Us

Johnson Tiles Harewood Street, Tunstall,

Stoke on Trent, Staffordshire, ST6 5JZ

Tel: +44 (0)1782 575 575 Fax: +44 (0)1782 577 377 Email: info@johnson-tiles.com

Samples Enquiries

Tel: +44 (0) | 782 524 043 Fax: +44 (0) | 782 577 379

Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | | | Fax: +44 (0) | | 782 577 379

Email: techadvice@johnson-tiles.com

